

## TECHNICAL DATA SHEET

**CELOCOR® AF***Opacifier***PRODUCT APPLICATION DETAILS**

Ammonia-free, voided latex particle that imparts hiding and acts as a partial replacement for titanium dioxide.

**SALES SPECIFICATIONS**

	CHARACTERISTICS	METHODS
Solid content	30.0 %	-
pH	8.0 - 9.0	-
Viscosity (#3 spindle @ 60 rpm. Brookfield LV)	100 cP	-

**OTHER CHARACTERISTICS<sup>1</sup>**

	CHARACTERISTICS	METHODS
Minimum film formation temperature	NA	-
Density	8.6	-

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

**MARKETS****Coatings & Inks**

- Graphic Arts
  - Inks
- Architectural Coating
  - Interior Wall
  - Trim
  - Interior Paints
  - Exterior Paints

# CELOCOR® AF

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

CELOCOR® AF - When storing and handling follow procedures recommended for polymer dispersions. Use corrosion resistant storage tanks and piping. Air-operated diaphragm pumps are preferred. Avoid temperature extremes. Do not freeze. Store between 40 to 90 °F (4 -32 °C). Packaged material should be stored indoors in a dry place in the original unopened and undamaged container. Exposure to direct sunlight should be avoided. The product is protected to prevent microbial deterioration during normal storage conditions; however, care should be taken to avoid accidental contamination during subsequent handling and processing. Bulk storage and handling practices are described in the Arkema Latex Storage and Handling Guide. For a copy of this guide contact Arkema.

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](http://arkema.com)

**Arkema Coating Resins**  
410 Gregson Dr.  
Cary, NC 27511 – USA  
T +1 919 469 6700

**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

**ARKEMA**