

TECHNICAL DATA SHEET

ECODIS™ P 30-30

Dispersing agent for water-based systems

Ionic Homopolymer dispersant

TYPICAL CHARACTERISTICS

Nature	Polyacrylate sodium salt
Appearance	Yellowish aqueous solution
Solid Content (%)	30
Active Content (%)	30
pH	8
Specific gravity	1.21
Neutralization type	Sodium
Solvent	Water

DESCRIPTION

Dispersion paints are usually formulated with fillers or extenders, particularly the very fine calcium carbonates and clays now available. Their dispersion in water based systems must be achieved easily with common stirrers without forming agglomerates or causing a viscosity build up. Usual inorganic dispersants such as phosphate based dispersants are not able to solve this problem satisfactorily: their deflocculating effectiveness is limited by the fineness of the extenders used and their poor temperature stability (degradation through hydrolysis) affects the long term stability of paints. Ecodis™ P 30-30 has been especially developed to overcome these problems. It ensures the complete dispersion of extenders and inorganic pigments at high solids contents in systems showing medium to high PVC (Pigment Volume Concentration).

RECOMMENDED ADDITION LEVEL

The required amount varies from 0.1% to 0.6% of active ingredients based on the total weight of the pigments and fillers. A more easy way is to start formulation trials using 0.5% to 0.6% of Ecodis™ P 30-30, as delivered, on the total formulation weight. It is recommended to disperse the pigments in a pH range between 7.0 and 9.5.

STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC
- 220L Drum
- Bulk

HANDLING & STORAGE

It should be protected from the effects of weathering and stored between 5 and 40°C.

Once opened, packaging should be resealed immediately after use.

In these conditions, this product should be used within 12 months from delivery.

MARKETS

Composites & Advanced Materials

- Graphic Arts

Coatings & Inks

- Architectural Coating
- Textile & Leather Coating
- Traffic Paint

Adhesives & Sealants

- Assembly
- Sealants

KEY BENEFITS

FORMULATION

- Cost in use
- Compatibility
- Easy handling



STORAGE

- Antisettling
- Viscosity stability
- Floating resistance
- Syneresis resistance



FILM PROPERTIES

- Hiding power/Opacity
- Gloss



SAFER SOLUTIONS

- APEO Free*
- Heavy Metal Free*
- Solvent Free*

* Not intentionally added but not specifically measured (not part of product specification)

PVC

PVC Low
PVC Mid
PVC High



SUITABLE FOR

Inorganic pigments
Fillers



ECODIS™ P 30-30

PROCESSING INSTRUCTIONS

Ecodis™ P 30-30 should be preferably added to water before the pigment incorporation. The optimum level is determined for each pigment blend by plotting the graph of the viscosities of the pigment dispersion in water, versus the amount of dispersant. The level of dispersant corresponding to the minimum viscosity is chosen.

HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA