

## TECHNICAL DATA SHEET

# ECODIS™ PE 620

Dispersing agent for water-based systems

## Ionic Homopolymer dispersant

### TYPICAL CHARACTERISTICS

Nature	<b>Polyacrylate Ammonium Salt</b>
Appearance	<b>Red to brown</b>
Solid Content (%)	<b>50</b>
Active Content (%)	<b>50</b>
pH	<b>8.5</b>
Specific gravity	<b>1.2</b>
Neutralization type	<b>Ammonium</b>
Solvent	<b>Water</b>

### DESCRIPTION

Polycarboxylic acid in aqueous solution

### RECOMMENDED ADDITION LEVEL

The required amount varies from 0.1% to 0.5% of active ingredients based on the total weight of the pigments and fillers. A more easy way is to start formulation trials using 0.4% to 0.5% of Ecodis™ PE 620, as delivered, on the total formulation weight. It is recommended to disperse the pigments in a pH range between 7.0 and 9.5.

### STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC • 220L Drum

### HANDLING & STORAGE

It should be protected from the effects of weathering and stored between 5 and 40°C. Once opened, packaging should be resealed immediately after use. In these conditions, this product should be used within 12 months from delivery.

### PROCESSING INSTRUCTIONS

Ecodis™ PE 620 should be preferably added to water before the pigment incorporation. The optimum level is determined for each pigment blend by plotting the graph of the viscosities of the pigment dispersion in water, versus the amount of dispersant. The level of dispersant corresponding to the minimum viscosity is chosen.

### HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

### MARKETS

#### Composites & Advanced Materials

- Graphic Arts

#### Coatings & Inks

- Architectural Coating
- Textile & Leather Coating
- Traffic Paint

#### Adhesives & Sealants

- Assembly
- Sealants

### KEY BENEFITS

#### FORMULATION

- Cost in use
- Easy handling
- Ready to use



#### STORAGE

- Antisettling
- Floating resistance
- Syneresis resistance
- Viscosity stability



#### FILM PROPERTIES

- Hiding power/Opacity



#### SAFER SOLUTIONS

- APEO Free\*
- Heavy Metal Free\*
- Solvent Free\*

\* Not intentionally added but not specifically measured (not part of product specification)

### PVC

- PVC Low
- PVC Mid
- PVC High



### SUITABLE FOR

- Fillers
- Inorganic pigments



**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80