

TECHNICAL DATA SHEET

ENCOR® 2222

Acrylic Emulsion

PRODUCT APPLICATION DETAILS

ENCOR® 2222 is a versatile pure acrylic emulsion formulated without alkylphenolethoxylates. ENCOR® 2222 is designed to be used as binder for high quality exterior paints.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (105°C)	45 - 47 %	ISO 3251
pH	8.5 - 9.5	ISO 976
Viscosity (Brookfield RVT , 20rpm) (23°C)	2500 - 5500 mPa.s	ISO 2555

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Stabilizing system	A / NI	
Minimum film formation temperature	6 °C	ISO 2115
Density	1.07 g/ml	ISO 2811
Average particle size	180 nm	ISO 13321
Freeze thaw stability	- 5 °C	ISO 1147

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Architectural Coating
 - Exterior Wall
 - Interior Wall
 - Primers
 - Specialty Coatings
- Textile & Leather Coating
 - Leather

ENCOR[®] 2222

FORMULATION GUIDELINES

RHEOLOGY

Rheology and viscosity can be adjusted using associative thickeners, such as Coapur[™] 830 W ⁽¹⁾ or Rheolate[®] 278 ⁽²⁾. Cellulosic thickeners are also adapted, namely Natrosol[®] 250 HHR ⁽³⁾.

OTHER ADDITIVES

Despite its low MFFT, coalescing agents, such as Texanol[®] ⁽⁴⁾ can be added to the formulation in order to improve the film formation, especially when applied in drastic conditions (low temperature and / or low relative humidity). The use of defoamers is recommended, Foamaster[®] MO 2134 ⁽⁵⁾ has proved to be efficient.

Notes: ⁽¹⁾ Coatex, ⁽²⁾ Elementis Specialties, ⁽³⁾ Ashland Specialty Ingredients, ⁽⁴⁾ Eastman Chemical Company, ⁽⁵⁾ BASF

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

ENCOR[®] 2222 should be stored indoors in the original, unopened and undamaged container, in a dry place at storage temperatures between 5°C and 30°C. Exposure to direct sunlight should be avoided. The product is protected to prevent any microbial deterioration during normal conditions of storage but care should be taken to avoid accidental contamination during subsequent handling and processing. In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Shelf Life (Months): 6

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

ARKEMA