ENCOR®

TECHNICAL DATA SHEET

ENCOR® 651

Acrylic Emulsion

PRODUCT APPLICATION DETAILS

Binder offering excellent overall performance and durability in athletic surface coatings.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	65.0 %	-
pH	9.1	-
Viscosity (#3 spindle @ 60 rpm. Brookfield LV)	500 cP	-

OTHER CHARACTERISTICS[1]

	CHARACTERISTICS	METHODS
Minimum film formation temperature	9 °C	-
Glass transition temperature (DSC)	12 °C	-
Density	8.7	-
Average particle size	350 nm	-

[1] The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Architectural Coating
  - Atheletic Surface Coatings
  - Exterior Wall
  - Primers
  - Specialty Coatings

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

ENCOR® 651 - When storing and handling follow procedures recommended for polymer dispersions. Use corrosion resistant storage tanks and piping. Air-operated diaphragm pumps are preferred. Avoid temperature extremes. Do not freeze. Store between 40 to 90 °F (4 -32 °C). Packaged material should be stored indoors in a dry place in the original unopened and undamaged container. Exposure to direct sunlight should be avoided. The product is protected to prevent microbial deterioration during normal storage conditions; however, care should be taken to avoid accidental contamination during subsequent handling and processing. Bulk storage and handling practices are described in the Arkema Latex Storage and Handling Guide. For a copy of this guide contact Arkema.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on https://www.arkema.com/global/en/products/product-safety/disclaimer/ which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790