POLYES®

TECHNICAL DATA SHEET

Poly Es® QE2184S/37

PRODUCT APPLICATION DETAILS

Poly ES QE-2184 S-37 is a carboxylic acrylic styrene copolymer, specifically designed for the production of printing pastes and textile finishes, as it possesses special properties and characteristics.
Has good mechanic stability
The poduct forms a very soft film

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	36.0 - 38.0 %	Internal method
pH	8.0 - 9.0	Internal method
Viscosity	10 - 150 cP	Internal method

OTHER CHARACTERISTICS[1]

	CHARACTERISTICS	METHODS
Appearance	Blueish white emulsion	
Glass transition temperature	-23 °C	
Density	1.02 g.cm	
Average particle size	0.16 microns	
Ionic charge	Anionic	

[1] The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS & APPLICATIONS

COATINGS & INKS

- ARCHITECTURAL COATING
  - EXTERIOR PAINTS

POLY ES® QE2184S/37

STORAGE AND HANDLING

Poly Es® QE2184S/37 Under normal conditions, the product has excellent stability. It is advisable to keep it indoors and away from sources of heat and UV radiation. We recommend using this product within 6 months of storage.
Shelf Life (Months): 6

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on https://www.arkema.com/global/en/products/product-safety/disclaimer/ which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

arkema.com