

TECHNICAL DATA SHEET

Poly VAK® QR320C

PRODUCT APPLICATION DETAILS

PolyVAK QR-320 C is a self-crosslinking carboxylic vinyl acrylic copolymer that, due to its chemical composition, forms cross-linked chains on the treated material, as it has special properties and characteristics.
Has good mechanic stability
The product forms a rigid film
No use of catalysts

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	44.0 - 46.0 %	Internal method
pH	2.5 - 4.5	Internal method
Viscosity	30 - 100 cP	Internal method

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Appearance	Blueish white emulsion	
Glass transition temperature	37 °C	
Density	1.06 g.cm	
Average particle size	0.25 microns	
Ionic charge	Anionic	

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS & APPLICATIONS

COATINGS & INKS

- ARCHITECTURAL COATING
- EXTERIOR PAINTS

POLY VAK® QR320C

STORAGE AND HANDLING

Poly VAK® QR320C Under normal conditions, the product has excellent stability. It is advisable to keep it indoors and away from sources of heat and UV radiation. We recommend using this product within 6 months of storage.
Shelf Life (Months): 6

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790