

## TECHNICAL DATA SHEET

# Poly VIL® QVG5235

### PRODUCT APPLICATION DETAILS

Poly VIL QVG-5235 is a rigid vinyl acetate homopolymer specially designed for the manufacture of adhesives and for use in textiles, as it has very special properties and characteristics.

Has good mechanic stability

The product forms a rigid film

High agglutination of fillers and pigments.

### SALES SPECIFICATIONS

|               | CHARACTERISTICS  | METHODS         |
|---------------|------------------|-----------------|
| Solid content | 34.0 - 36.0 %    | Internal method |
| pH            | 4.0 - 6.0        | Internal method |
| Viscosity     | 2,000 - 6,000 cP | Internal method |

### OTHER CHARACTERISTICS<sup>1</sup>

|              | CHARACTERISTICS        | METHODS |
|--------------|------------------------|---------|
| Appearance   | White viscous emulsion |         |
| Density      | 1.05 g.cm              |         |
| Ionic charge | Non anionic            |         |

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### MARKETS & APPLICATIONS

#### COATINGS & INKS

- ARCHITECTURAL COATING
- EXTERIOR PAINTS

# POLY VIL® QVG5235

## STORAGE AND HANDLING

Poly VIL® QVG5235 Under normal conditions, the product has excellent stability. It is advisable to keep it indoors and away from sources of heat and UV radiation. We recommend using this product within 6 months of storage.  
Shelf Life (Months): 6

**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790