

## TECHNICAL DATA SHEET

# REAFREE® 4796

Powder Resins / Saturated Carboxylated Polyester / TGIC

### PRODUCT APPLICATION DETAILS

Saturated carboxylated polyester for combination with Triglycidylisocyanurate. Suitable for the formulation of decorative and protective thermosetting powders for electrostatic application. Slow curing type. TMA free type.

### SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Acid value	30-36 mg KOH/g	ASTM D-1639
Viscosity (Cone and plate - 165°C)	25-40 Pa.s	DIN 53229
Color (50%)	2 max Gardner	ASTM D-1544

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Appearance	Pale granules	
Glass transition temperature (T <sub>g</sub> )	approx 68 °C	DSC

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### CURING CONDITIONS

10 minutes at 200°C (object temperature)

### RECOMMENDED MIXING RATIO

REAFREE® 4796 / TGIC: 93/7

### MARKET & APPLICATIONS

#### Health, Hygiene, & Beauty

- Detergency & Cleaning
  - Textile & Others

#### Coatings & Inks

- Industrial Coating
  - General Industry
  - Metal Exterior - Powder
  - Metal Interior - Powder
  - Protective Coating

### PERFORMANCE BENEFITS

- Very good flow.
- High gloss.
- Good mechanical properties.
- Excellent outdoor durability.

# REAFREE® 4796

## FORMULATION GUIDELINES

STARTING FORMULATION	
<b>REAFREE® 4796</b>	595
Titanium Dioxide <sup>(1)</sup>	320
Triglycidylisocyanurate <sup>(2)</sup>	45
<b>REAFREE® F3300-A15</b>	37
Benzoin	3

<sup>(1)</sup> Kronos® 2160

<sup>(2)</sup> Araldite® PT-810 (Huntsman) / Tepic (Nissan Chemical)

## APPLICATION / EXTRUSION CONDITIONS

CHARACTERISTICS	
Extruder	BUSS PCS-30
Spraying gun	GEMA PG 1-B
Torque	40 %
Extrusion speed	200 rpm
Application voltage	60-80 kV
Test substrate (Degreased steel)	1 mm
Extrusion temperature	80 °C

## COATING PROPERTIES

	CHARACTERISTICS	METHODS
Film thickness	60-80 microns	
Gloss (60°)	Over 90 %	
Cupping test	Over 8 mm	DIN 53156
Direct impact	Over 80 kg.cm	ASTM D-2794
Reverse impact	Over 80 kg.cm	ASTM D-2794
Conical mandrel	100 %	ASTM D-522
Adhesion	Gt0	DIN 53151

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## DELIVERY FORM

Granules. White opaque polyethylene bags of 25 Kg. One Ton pallet shrink – wrapped.

## STORAGE AND HANDLING

The resin in its original unopened bags is stable for more than three years, stored in a dry place at temperature below 30°C. Avoid direct sunlight.

**Arkema Coating Resins**  
410 Gregson Dr.  
Cary, NC 27511 – USA  
T +1 919 469 6700

**Arkema Química, S.A.U.**  
Ctra. Olzinelles, s/n  
E-08470 Sant Celoni (BCN)  
Spain  
T +34 938 674 000

**Arkema Chemical India Private Ltd.**  
D-43, Trans Thane Creek  
MIDC Industrial Area  
400706 Mumbai - India  
T +91 22 67377122

**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](http://arkema.com)

**ARKEMA**