

TECHNICAL DATA SHEET

REAFREE® 5002

Powder Resins / Saturated Carboxylated Polyester / TGIC and β -Hydroxyalkylamide



PRODUCT APPLICATION DETAILS

Saturated carboxylated polyester for combination with Triglycidylisocyanurate or β -Hydroxyalkylamide type hardeners. Suitable for the formulation of outdoor SUPERDURABLE and protective thermosetting powders for electrostatic application. For mat paints by dry-blend with REAFREE 5401. High cross-linking density. TMA free type.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Acid value	45-50 mg KOH/g	ASTM D-1639
Viscosity (Cone and plate - 165°C)	30-60 Pa.s	DIN 53229
Color (50%)	2 max Gardner	ASTM D-1544

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Appearance	Pale granules	
Glass transition temperature (Tg)	approx 66 °C	DSC

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

CURING CONDITIONS

TGIC: 15 minutes at 200°C (object temperature)
PRIMID⁽¹⁾: 20 minutes at 160°C; 10 minutes at 180°C (object temperature)
⁽¹⁾ EMS-Chemie AG

RECOMMENDED MIXING RATIO

REAFREE® 5002 / TGIC: 90/10
REAFREE® 5002 / PRIMID XL-552⁽¹⁾: 93/7
⁽¹⁾ EMS-Chemie AG

MARKET & APPLICATIONS

Coatings & Inks

- Industrial Coating
 - Ace
 - General Industry
 - Metal Exterior - Powder
 - Metal Interior - Powder

PERFORMANCE BENEFITS

- Good flow.
- Good mechanical properties.
- Excellent outdoor durability.

REAFREE® 5002

FORMULATION GUIDELINES

	STARTING FORMULATION	
	A	B
REAFREE® 5002	576	-
REAFREE® 5401	-	614
Titanium Dioxide ⁽¹⁾	320	320
Triglycidylisocyanurate ⁽²⁾	64	26
REAFREE® F3300-A15	37	37
Benzoin	3	3

⁽¹⁾ Kronos® 2160

⁽²⁾ Araldite® PT-810 (Hunstman) / Tetric (Nissan Chemical)

DRY-blend paints A/B: 50/50

APPLICATION / EXTRUSION CONDITIONS

	CHARACTERISTICS
Extruder	BUSS PCS-30
Spraying gun	GEMA PG 1-B
Torque	40 %
Extrusion speed	200 rpm
Application voltage	60-80 kV
Test substrate (Degreased steel)	1 mm
Extrusion temperature	80 °C

COATING PROPERTIES

	CHARACTERISTICS	METHODS
Film thickness	60-80 microns	
Gloss (60°)	approx. 35 %	
Cupping test	Over 8 mm	DIN 53156
Direct impact	Over 50 kg.cm	ASTM D-2794
Reverse impact	Over 20 kg.cm	ASTM D-2794
Conical mandrel	100 %	ASTM D-522
Adhesion	Gt0	DIN 53151

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

DELIVERY FORM

Granules. White opaque polyethylene bags of 25 Kg. One Ton pallet shrink – wrapped.

STORAGE AND HANDLING

The resin in its original unopened bags is stable for more than three years, stored in a dry place at temperature below 30°C. Avoid direct sunlight.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Arkema Química, S.A.U.
Ctra. Olzinelles, s/n
E-08470 Sant Celoni (BCN)
Spain
T +34 938 674 000

Arkema Chemical India Private Ltd.
D-43, Trans Thane Creek
MIDC Industrial Area
400706 Mumbai - India
T +91 22 67377122

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

arkema.com

ARKEMA