

## TECHNICAL DATA SHEET

# REAFREE® 5401

Powder Resins / Saturated Carboxylated Polyester / TGIC and  $\beta$ -Hydroxyalkylamide



Superdurable

### PRODUCT APPLICATION DETAILS

Saturated carboxylated polyester for combination with Triglycidylisocyanurate or  $\beta$ -Hydroxyalkylamide type hardeners. Suitable for the formulation of outdoor SUPERDURABLE and protective thermosetting powders for electrostatic application. For mat paints by dry-blend with REAFREE 5002 or REAFREE 5080. Low TGIC or PRIMID demand. TMA free type.

### SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Acid value	20-25 mg KOH/g	ASTM D-1639
Viscosity (Cone and plate - 165°C)	20-40 Pa.s	DIN 53229
Color (50%)	2 max Gardner	ASTM D-1544

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Appearance	Pale granules	
Glass transition temperature (Tg)	approx 64 °C	DSC

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### CURING CONDITIONS

PRIMID<sup>(1)</sup>: 12 minutes at 180°C (object temperature)

TGIC: 15 minutes at 200°C (object temperature)

<sup>(1)</sup> EMS-Chemie AG

### RECOMMENDED MIXING RATIO

REAFREE® 5401 / PRIMID XL-552<sup>(1)</sup>: 97/3

REAFREE® 5401 / TGIC: 96/4

<sup>(1)</sup> EMS-Chemie AG

### MARKET & APPLICATIONS

#### Coatings & Inks

- Industrial Coating
  - Ace
  - General Industry
  - Metal Exterior - Powder
  - Metal Interior - Powder

### PERFORMANCE BENEFITS

- Good flow.
- Good mechanical properties.
- Excellent outdoor durability.

# REAFREE® 5401

## FORMULATION GUIDELINES

	STARTING FORMULATION	
	A	B
<b>REAFREE® 5401</b>	-	614
<b>REAFREE® 5002</b>	576	-
Titanium Dioxide <sup>(1)</sup>	320	320
Triglycidylisocyanurate <sup>(2)</sup>	64	26
<b>REAFREE® F3300-A15</b>	37	37
Benzoin	3	3

<sup>(1)</sup> Kronos® 2160

<sup>(2)</sup> Araldite® PT-810 (Huntsman) / Tepic (Nissan Chemical)

DRY-blend paints A/B: 50/50

## APPLICATION / EXTRUSION CONDITIONS

	CHARACTERISTICS
Extruder	BUSS PCS-30
Spraying gun	GEMA PG 1-B
Torque	40 %
Extrusion speed	200 rpm
Application voltage	60-80 kV
Test substrate (Degreased steel)	1 mm
Extrusion temperature	80 °C

## COATING PROPERTIES

	CHARACTERISTICS	METHODS
Film thickness	60-80 microns	
Gloss (60°)	approx. 35 %	
Cupping test	Over 8 mm	DIN 53156
Direct impact	Over 50 kg.cm	ASTM D-2794
Reverse impact	Over 20 kg.cm	ASTM D-2794
Conical mandrel	100 %	ASTM D-522
Adhesion	Gt0	DIN 53151

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## DELIVERY FORM

Granules. White opaque polyethylene bags of 25 Kg. One Ton pallet shrink – wrapped.

## STORAGE AND HANDLING

The resin in its original unopened bags is stable for more than three years, stored in a dry place at temperature below 30°C. Avoid direct sunlight.

**Arkema Coating Resins**  
410 Gregson Dr.  
Cary, NC 27511 – USA  
T +1 919 469 6700

**Arkema Química, S.A.U.**  
Ctra. Olzinelles, s/n  
E-08470 Sant Celoni (BCN)  
Spain  
T +34 938 674 000

**Arkema Chemical India Private Ltd.**  
D-43, Trans Thane Creek  
MIDC Industrial Area  
400706 Mumbai - India  
T +91 22 67377122

**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](http://arkema.com)

**ARKEMA**