

## TECHNICAL DATA SHEET

# RHEOTECH™ 146

Acrylic thickener for water-based systems

## ASE Acrylic Thickener

### TYPICAL CHARACTERISTICS

Nature	<b>Aqueous dispersion of an acrylic copolymer</b>
Appearance	<b>Low viscous white milky liquid</b>
Solid Content (%)	<b>28</b>
Active Content (%)	<b>28</b>
pH	<b>3</b>
Specific gravity	<b>1.05</b>
Solvent	<b>Water</b>

### DESCRIPTION

Rheotech™ 146 is a non associative thickener designed for use in adhesives, paints, sealants and mastics.

### RECOMMENDED ADDITION LEVEL

Typical addition level is between 0.2 to 1.5 % as supplied on total formulation weight.

### STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC
- 200L Drum
- Bulk

### HANDLING & STORAGE

It can be irreversibly altered by frost. It should be protected from the effects of weathering and stored between 5 and 40°C and protected from direct sun exposure.

Once opened, packaging should be resealed immediately after use.

In these conditions, this product should be used within 6 months from delivery.

### PROCESSING INSTRUCTIONS

Supplied as a low viscosity liquid emulsion, it is very easy to handle. No predissolution, elimination of lumps or warming required. May be used either at the beginning of the formulation or in the pigment grinding or in the finished product to adjust the final viscosity. Rheotech™ 146 can be used in many kinds of aqueous adhesives, paints, sealants & mastics. The pH of the formulated product must be controlled to obtain good performance and reproducible viscosity.

### MARKETS

#### Composites & Advanced Materials

- Graphic Arts

#### Coatings & Inks

- Architectural Coating
- Industrial Coating
- Textile & Leather Coating

#### Adhesives & Sealants

- Assembly
- Sealants
- Wet Glue Adhesive
- Wood Adhesive

### KEY BENEFITS

#### FORMULATION

- Cost in use
- Easy handling
- Color acceptance



#### STORAGE

- Syneresis resistance
- Antisettling
- In-can appearance
- Viscosity stability



#### APPLICATION

- Brushability
- Rollability
- Sag resistance



#### FILM PROPERTIES

- Gloss
- Rub out
- Stain resistance



#### SAFER SOLUTIONS

- APEO Free\*
- Heavy Metal Free\*
- Solvent Free\*

\* Not intentionally added but not specifically measured (not part of product specification)

### THICKENING MECHANISM

Non Associative  
Self Association  
Associative



# RHEOTECH™ 146

## HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

## VISCOSITY CONTRIBUTION

Low Shear contribution   
Mid Shear contribution   
High Shear contribution 

## PVC

PVC Low   
PVC Mid   
PVC High 

**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**