

## TECHNICAL DATA SHEET

# SYNAQUA® 4804 NA

*Alkyd Emulsion*

### PRODUCT APPLICATION DETAILS

SYNAQUA® 4804 NA is a short oil alkyd emulsion designed for high performance low yellowing decorative coatings. SYNAQUA® 4804 NA is low VOC capable but provides performance similar to solvent-based alkyds.

It is dedicated to interior and exterior trim paints, interior wall paints and metal primers.

SYNAQUA® 4804 NA is APEO-, ammonia-, solvent- and plasticizer- free.

### SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	49 - 51 %	-
Viscosity (#1 spindle @ 10 rpm. 23+/-2°C. Brookfield. LV)	300 cP	-
Color	Milky white	-

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Solvent	Water	-
Density	8.9	-
Average particle size	300 max nm	-

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### MARKETS

#### Coatings & Inks

- Architectural Coating
  - Exterior Wall
  - Interior Wall
  - Primers
  - Specialty Coatings
  - Stains
  - Trim
- Flooring
  - Floor Polish & Floor Coatings
- Industrial Coating
  - General Industry

# SYNAQUA® 4804 NA

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

SYNAQUA® 4804 NA - When storing and handling follow procedures recommended for polymer dispersions. Use corrosion resistant storage tanks and piping. Air-operated diaphragm pumps are preferred. Avoid temperature extremes. Do not freeze. Store between 40 to 90 °F (4 -32 °C). Packaged material should be stored indoors in a dry place in the original unopened and undamaged container. Exposure to direct sunlight should be avoided. The product is protected to prevent microbial deterioration during normal storage conditions; however, care should be taken to avoid accidental contamination during subsequent handling and processing. Bulk storage and handling practices are described in the Arkema Latex Storage and Handling Guide. For a copy of this guide contact Arkema.

**Arkema Coating Resins**  
410 Gregson Dr.  
Cary, NC 27511 – USA  
T +1 919 469 6700

**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

**ARKEMA**