

TECHNICAL DATA SHEET

SYNOCURE® 225 BA 50 MY

Acrylic polyol

PRODUCT APPLICATION DETAILS

SYNOCURE® 225 BA 50 MY is a hydroxy functional acrylic resin supplied in butyl acetate that will allow the formulation of aromatic-free systems.

SYNOCURE® 225 BA 50 MY is particularly recommended for fast drying wood coatings but also suitable for industrial finishes and primers.

SYNOCURE® 225 BA 50 MY is especially suitable for coatings in the furniture industry exhibiting excellent chemical resistance and mechanical properties.

SYNOCURE® 225 BA 50 MY exhibits a faster hardening rate than similar resins resulting in early blocking resistance of the applied films under ambient or force dry conditions without compromising the good flexibility.

The long pot life of the prepared mixture offers easy processing on all types of industrial coating equipment.

SALES SPECIFICATIONS

| | CHARACTERISTICS | METHODS |
|---|-----------------|----------|
| Solid content (125°C, %) | 49 - 51 | ISO 3251 |
| Viscosity (Brookfield SSA 34/13R, 3.36 s-1) (25°C, mPa.s) | 2700 - 4000 | ISO 3219 |
| Color (Hazen) | 50 max | ISO 6271 |
| Acid value (mg KOH/g) | 14 - 24 | ISO 2114 |

OTHER CHARACTERISTICS¹

| | CHARACTERISTICS | METHODS |
|----------------------|-----------------|---------|
| Solvent | Butyl Acetate | - |
| Density (25°C, g/mL) | 1 | - |
| Hydroxyl content (%) | 2 | - |

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS & APPLICATIONS

Coatings & Inks

- Industrial Coating
 - Automotive - Refinish
 - General Industry
 - Plastics
 - Wood Furniture
 - Industrial Wood Finishes
 - Metal Exterior

SYNOCURE® 225 BA 50 MY

FORMULATION GUIDELINES

RECOMMENDATIONS FOR USE

SYNOCURE® 225 BA 50 MY is compatible with most aliphatic or aromatic polyisocyanates.

SYNOCURE® 225 BA 50 MY may be reacted with most aliphatic and aromatic polyisocyanates, like Desmodur® N 75, N 3390, L, HL, IL ⁽¹⁾ or Tolonate™ HDB 75 MX ⁽²⁾.

Due to the quick physical drying of SYNOCURE® 225 BA 50 MY an addition of catalysts is normally not required.

SYNOCURE® 225 BA 50 MY may be pigmented with all neutral pigments and extenders. It exhibits very good pigment acceptance which results in very good gloss levels.

The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants.

The relationship is:

Hydroxyl Equivalent Weight = $(17 \times 100) / \%OH$

Isocyanate Equivalent Weight = $(42 \times 100) / \%NCO$

SOLUBILITY

SYNOCURE® 225 BA 50 MY maybe thinned in all solvents suitable for 2K-PU-systems, like xylene, esters, ether esters and ketones. It has a limited solubility in aromatic hydrocarbons.

COMPATIBILITY

SYNOCURE® 225 BA 50 MY is compatible with cellulose acetate butyrates, nitrocellulose, some PVC-copolymers.

Notes: ⁽¹⁾ Covestro, ⁽²⁾ VENCOREX® Chemicals

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOCURE® 225 BA 50 MY should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 12 months.

Arkema Coating Resins Malaysia
PLO 491, Jalan Keluli, Pasir Gudang
Industrial Estate, 81700 Pasir Gudang,
Johor – Malaysia
T +60 7 253 6688

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790