

TECHNICAL DATA SHEET

SYNOCURE® 853 BA 80

Acrylic polyol

PRODUCT APPLICATION DETAILS

SYNOCURE® 853 BA 80 is a high solids hydroxy functional acrylic resin designed for curing at both room temperature and under low bake conditions with suitable polyisocyanates.

Ease of application, initial gloss and appearance make them suitable for many applications including ACE and general metal coatings. Coatings based on SYNOCURE® 853 BA 80 are faster drying than most other high solids types.

The high solids/low viscosity character of SYNOCURE® 853 BA 80 allows low VOC coatings to be formulated even with conventional polyisocyanates. Depending upon formulation <420g/l at 23 seconds and <350g/l at 45 seconds are possible.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C)	78 - 82 %	ISO 3251
Viscosity (25°C)	13000 - 17000 mPa.s	ISO 12058-1
Color	2 max Gardner	ISO 4630
Acid value	10 max mg KOH/g	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Butyl acetate	-
Flash point	23 °C	ISO 3679
Density	1.035 g/ml	ISO 2811
Hydroxyl content	4.1 %	-
Hydroxyl equivalent weight	415	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - General Industry

SYNOCURE® 853 BA 80

FORMULATION GUIDELINES

RECOMMENDATIONS FOR USE

SYNOCURE® 853 BA 80 should be mixed just prior to application with the selected polyisocyanate. The mixing ratio is not critical although it is preferable to use stoichiometric ratios to obtain optimum performance.

The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants.

The relationship is:

Hydroxyl Equivalent Weight = $(17 \times 100) / \%OH$

Isocyanate Equivalent Weight = $(42 \times 100) / \%NCO$

Using Desmodur® N 75 series ⁽¹⁾ or Tolonate™ HDB 75 MX ⁽²⁾, the recommended ratios would be:

- on solid resins: SYNOCURE® 853 BA 80/Desmodur® N 75 series ⁽¹⁾ or Tolonate™ HDB 75 MX ⁽²⁾ = 415/191

- as supplied: SYNOCURE® 853 BA 80/Desmodur® N 75 series ⁽¹⁾ or Tolonate™ HDB 75 MX ⁽²⁾ = 519/255

The high reactivity of systems based on SYNOCURE® 853 BA 80 makes them ideal for use in coatings applied with twin-feed guns. When conventional application equipment is used care should be taken to mix no more paint than can be applied during the period appropriate to the pot life and to clean equipment immediately after use.

If necessary the initial rate of cure of SYNOCURE® 853 BA 80 based systems can be accelerated by the use of tin catalyst in the form of dibutyltin dilaurate. Although the level can be varied to suit specific requirements 0.003% metal based on total solid resin is a good starting point.

SYNOCURE® 853 BA 80 should only be used in applications consistent with the above recommendations. Proposals to use the resin in alternative ways should be discussed with Arkema before any action is taken.

SOLUBILITY

The solvents chosen for paints and lacquers based on SYNOCURE® 853 BA 80 should be free of water and should not contain groups that react with isocyanates.

Esters and ketones are true solvents for this type of system and are recommended for use in conjunction with aromatic hydrocarbon diluents such as xylene.

Notes: ⁽¹⁾ Bayer MaterialScience, ⁽²⁾ VENCOREX® Chemicals

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOCURE® 853 BA 80 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Shelf Life (Months): 12

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790