

## TECHNICAL DATA SHEET

# SYNOCURE® 867 BA 60 MY

*Acrylic polyol*

### PRODUCT APPLICATION DETAILS

SYNOCURE® 867 BA 60 MY is a hydroxy functional acrylic designed to crosslink at room temperature with polyisocyanates.

SYNOCURE® 867 BA 60 MY is especially recommended for coatings where outdoor durability and resistant properties are of prime importance.

### SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C, %)	58 - 62	ISO 3251
Viscosity (25°C, mPa.s)	3500 - 6000	ISO 3219
Color (Hazen)	70 max	ISO 6271
Acid value (mg KOH/g)	8 max	ISO 2114

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Solvent	Butyl acetate	-
Density (25°C, g/mL)	1.02	-
Hydroxyl content (%)	2.8	-
Hydroxyl equivalent weight	600	-

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### MARKETS

#### Coatings & Inks

- Industrial Coating
  - Automotive - Refinish
  - General Industry
  - Protective Coating
  - Protective And Marine Coating
  - Wood Furniture

### PERFORMANCE BENEFITS

- Excellent chemical and stain resistance
- Good durability
- Excellent adhesion
- Long pot life

# SYNOCURE® 867 BA 60 MY

## FORMULATION GUIDELINES

### RECOMMENDATIONS FOR USE

SYNOCURE® 867 BA 60 MY should be mixed with the selected polyisocyanate just prior to application. The mixing ratio is not critical, although it is preferable to use stoichiometric ratios to obtain optimum performance.

The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants. The relationship is:

Hydroxyl Equivalent Weight =  $(17 \times 100) / \%OH$

Isocyanate Equivalent Weight =  $(42 \times 100) / \%NCO$

Using Desmodur® N 75 series <sup>(1)</sup> or Tolonate™ HDB 75 MX <sup>(2)</sup>, the recommended ratios would be:

- on solid resins: SYNOCURE® 867 BA 60 MY/Desmodur® N 75 series <sup>(1)</sup> or Tolonate™ HDB 75 MX <sup>(2)</sup> = 600/191

- as supplied: SYNOCURE® 867 BA 60 MY/Desmodur® N 75 series <sup>(1)</sup> or Tolonate™ HDB 75 MX <sup>(2)</sup> = 1000/255

When mixed with polyisocyanates in stoichiometric proportions, SYNOCURE® 867 BA 60 MY has a long usable pot life in normal room temperature. This usable period will be reduced in high temperature conditions or when catalysts are used.

The initial curing rate can be increased by the use of tin or zinc catalysts such as dibutyl tin dilaurate or zinc octoate. The levels used will depend on the specific requirements, but typical metal contents calculated on total solid resin are 0.001% tin and 0.0015% zinc.

Coatings prepared from SYNOCURE® 867 BA 60 MY and stoichiometric quantities of polyisocyanates will have sand dry times of approximately 15min and hard dry times of 1h to 3h.

### SOLUBILITY

Solvents used in systems containing SYNOCURE® 867 BA 60 MY should be low water content grades and not contain chemical groups (such as hydroxyl) which will react with isocyanates and thereby inhibit the film forming reaction. Esters and ketones are true solvents for this type of system, usually combined with aromatic hydrocarbon diluents.

Notes: <sup>(1)</sup> Covestro, <sup>(2)</sup> Vencorex Chemicals

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

SYNOCURE® 867 BA 60 MY should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 12 months.

**Arkema Coating Resins Malaysia**  
PLO 491, Jalan Keluli, Pasir Gudang  
Industrial Estate, 81700 Pasir Gudang,  
Johor – Malaysia  
T +60 7 253 6688

**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790