

TECHNICAL DATA SHEET

SYNOCURE® 867 S 57 MY

Acrylic polyol

PRODUCT APPLICATION DETAILS

SYNOCURE® 867 S 57 MY is a hydroxy functional acrylic resin designed to crosslink at room temperature with polyisocyanates.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C, %)	55 - 59	ISO 3251
Viscosity (25°C, mPa.s)	3000 - 5000	ISO 3219
Color (Hazen)	70 max	ISO 6271
Acid value (mg KOH/g)	6 max	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Xylene and methoxy propyl acetate (3:1)	-
Density (25°C, g/mL)	1.01	-
Hydroxyl content (%)	2.8	-
Hydroxyl equivalent weight	600	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS & APPLICATIONS

Coatings & Inks

- Industrial Coating
 - Automotive - Refinish
 - General Industry
 - Protective And Marine Coating
 - Wood Furniture

PERFORMANCE BENEFITS

- Excellent chemical and stain resistance
- Good durability
- Excellent adhesion
- Long pot life

SYNOCURE® 867 S 57 MY

FORMULATION GUIDELINES

RECOMMENDATIONS FOR USE

SYNOCURE® 867 S 57 MY should be mixed just prior to application with the selected polyisocyanate. The mixing ratio is not critical although it is preferable to use stoichiometric ratios to obtain optimum performance.

The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants. The relationship is:

Hydroxyl Equivalent Weight = $(17 \times 100) / \%OH$

Isocyanate Equivalent Weight = $(42 \times 100) / \%NCO$

Using Desmodur® N 75 series ⁽¹⁾ or Tolonate™ HDB 75 MX ⁽²⁾, the recommended ratios would be:

- on solid resins: SYNOCURE® 867 S 57 MY/Desmodur® N 75 series ⁽¹⁾ or Tolonate™ HDB 75 MX ⁽²⁾ = 600/191

- as supplied: SYNOCURE® 867 S 57 MY/Desmodur® N 75 series ⁽¹⁾ or Tolonate™ HDB 75 MX ⁽²⁾ = 1000/255

At normal temperatures, the surface drying time of paints based on this combination is typically 15 min, with hard dry in 1h to 3h.

SYNOCURE® 867 S 57 MY reacted with Desmodur® N 75 series ⁽¹⁾ or Tolonate™ HDB 75 MX ⁽²⁾ in stoichiometric proportions has a long usable pot life at normal room temperature. The use of catalysts or higher temperatures will reduce this storage period.

To increase the initial rate of cure of SYNOCURE® 867 S 57 MY paints, at both ambient temperature and under low bake conditions, the use of tin or zinc catalysts in the form of dibutyl tin dilaurate or zinc octoate is recommended. The levels used will depend on specific requirements, but typical metal contents calculated on total solid resin would be 0.001% tin and 0.0015% zinc.

SOLUBILITY

The solvents chosen for paints and lacquers based on SYNOCURE® 867 S 57 MY should be free of water and should not contain groups which react with isocyanates. Esters and ketones are true solvents for this type of system and are usually used with aromatic hydrocarbon diluents.

Notes: ⁽¹⁾ Covestro, ⁽²⁾ Vencorex Chemicals

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOCURE® 867 S 57 MY should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 12 months.

Arkema Coating Resins Malaysia
PLO 491, Jalan Keluli, Pasir Gudang
Industrial Estate, 81700 Pasir Gudang,
Johor – Malaysia
T +60 7 253 6688

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790