

TECHNICAL DATA SHEET

SYNOCURE® 871 X 60

Acrylic polyol

PRODUCT APPLICATION DETAILS

SYNOCURE® 871 X 60 is a hydroxy functional acrylic resin designed to crosslink with polyisocyanates at room temperature.

Paints and lacquers based on SYNOCURE® 871 X 60 are particularly suitable for coating plastic substrates.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C)	58 - 62 %	ISO 3251
Viscosity (25°C)	2000 - 3000 mPa.s	ISO 12058-1
Color	70 max Pt/Co	DIN EN 1557
Acid value	10 max mg KOH/g	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Xylene	-
Flash point	24 °C	ISO 3679
Density	1.02 g/ml	ISO 2811
Hydroxyl content	3.6 %	-
Hydroxyl equivalent weight	475	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - Automotive - OEM
 - Automotive - Refinish
 - Coil
 - General Industry

PERFORMANCE BENEFITS

- Good flexibility
- Excellent low temperature impact resistance
- Smooth, hard finishes

SYNOCURE® 871 X 60

FORMULATION GUIDELINES

RECOMMENDATIONS FOR USE

SYNOCURE® 871 X 60 should be mixed just prior to application with the selected polyisocyanate. The mixing ratio is not critical although it is preferable to use stoichiometric ratios to obtain optimum performance.

The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants.

The relationship is:

Hydroxyl Equivalent Weight = $(17 \times 100) / \%OH$

Isocyanate Equivalent Weight = $(42 \times 100) / \%NCO$

Using Desmodur® N 75 series ⁽¹⁾ or Tolonate™ HDB 75 MX ⁽²⁾, the recommended ratios would be:

- on solid resins: SYNOCURE® 871 X 60/Desmodur® N 75 series ⁽¹⁾ or Tolonate™ HDB 75 MX ⁽²⁾ = 475/191

- as supplied: SYNOCURE® 871 X 60/Desmodur® N 75 series ⁽¹⁾ or Tolonate™ HDB 75 MX ⁽²⁾ = 792/255

At normal temperatures, and catalysed with 0.004% tin, the surface drying time of paints based on this combination is typically 130 min, with hard dry in 4h.

To increase the initial rate of cure of SYNOCURE® 871 X 60 paints, at both ambient temperatures and under low bake conditions, the use of tin catalyst in the form of dibutyl tin dilaurate is recommended. The levels used will depend on specific requirements, but typical metal content calculated on total solid resin would be 0.001% tin or 0.004% tin.

SYNOCURE® 871 X 60 reacted with Desmodur® N 75 series ⁽¹⁾ or Tolonate™ HDB 75 MX ⁽²⁾ in stoichiometric proportions has a usable pot life at spraying viscosity in excess of a full working day at normal room temperature. The use of catalysts or higher temperatures will reduce this storage period.

SOLUBILITY

Solvents chosen for paints and lacquers based on SYNOCURE® 871 X 60 should be free of water and should not contain groups which react with isocyanates. Esters and ketones are true solvents for this type of system and are recommended for use in conjunction with aromatic hydrocarbon diluents such as xylene.

Notes: ⁽¹⁾ Bayer MaterialScience, ⁽²⁾ VENCOREX® Chemicals

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOCURE® 871 X 60 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

ARKEMA