

## TECHNICAL DATA SHEET

# SYNOCURE® 9277 S 65 MY

Acrylic polyol

### PRODUCT APPLICATION DETAILS

SYNOCURE® 9277 S 65 MY is a hydroxy functional acrylic designed to crosslink at room temperature or under low-bake conditions with aliphatic polyisocyanates. It is particularly recommended for use in vehicle refinishing, A.C.E., Transport coatings and Heavy Duty Coatings.

### SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C, %)	64 - 66	ISO 3251
Viscosity (25°C, mPa.s)	2500 - 4000	ISO 3219
Color (Hazen)	100 max	ISO 6271
Acid value (mg KOH/g)	10 max	ISO 2114

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Solvent	Butyl acetate and Xylene (3:1)	-
Density (25°C, g/mL)	1.02	-
Hydroxyl content (%)	4.2	-
Hydroxyl equivalent weight	400	-

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### MARKETS & APPLICATIONS

#### Coatings & Inks

- Industrial Coating
  - Automotive - Refinish
  - General Industry
  - Marine
  - Protective And Marine Coating
  - Wood Furniture

### PERFORMANCE BENEFITS

- Fast dry and good early hardness
- Good application properties
- Excellent mechanical properties
- Good weathering performance

# SYNOCURE® 9277 S 65 MY

## FORMULATION GUIDELINES

### RECOMMENDATIONS FOR USE

SYNOCURE® 9277 S 65 MY should be mixed with the selected polyisocyanate just prior to application. The mixing ratio is not critical although it is preferable to use stoichiometric ratios to obtain optimum performance.

The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants.

The relationship is:

Hydroxyl Equivalent Weight =  $(17 \times 100) / \%OH$

Isocyanate Equivalent Weight =  $(42 \times 100) / \%NCO$

Using Tolonate™ HDB 75 MX <sup>(1)</sup>, the recommended ratios would be:

- on solid resins: SYNOCURE® 9277 S 65 MY/Tolonate™ HDB 75 MX <sup>(1)</sup> = 400/191

- as supplied: SYNOCURE® 9277 S 65 MY/Tolonate™ HDB 75 MX <sup>(1)</sup> = 615/255

### SOLUBILITY

The solvents chosen for paints and lacquers based on SYNOCURE® 9277 S 65 MY used should be free from water and not contain groups that react with isocyanates. Esters and ketones are true solvents and are recommended for use in combination with aromatic hydrocarbon diluents such as xylene.

Notes: <sup>(1)</sup> VENCOREX® Chemicals

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

SYNOCURE® 9277 S 65 MY should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 12 months.

**Arkema Coating Resins Malaysia**  
PLO 491, Jalan Keluli, Pasir Gudang  
Industrial Estate, 81700 Pasir Gudang,  
Johor – Malaysia  
T +60 7 253 6688

**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

**ARKEMA**