

TECHNICAL DATA SHEET

SYNOLAC® 20108S-65

Oil free polyester

PRODUCT APPLICATION DETAILS

SYNOLAC® E20108-65 is a saturated polyester recommended for the formulation of cost effective coil and metal packaging coating applications.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (at 150°C, 1gm, 1hr)	64 - 66 %	ISO 3251
Viscosity (Brookfield Viscometer) (at 25°C)	33 - 39 P	ISO 3219
Color	3 max Gardner	ISO 4630
Acid value	10 max mg KOH/g	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Volatile	Aromatic solvent 100/Butyl Glycol (70:30)	
Flash point	40 °C	ISO 3679
Density (at 20°C)	1.07 g/ml	ISO 2811
Hydroxyl content	140 - 160 mg KOH/g	

Acid value and/or Hydroxyl value quoted relative to solid resin

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
- Coil

PERFORMANCE BENEFITS

- Capable of curing at high line speeds
- Combine good weatherability with good flexibility
- Good adhesion
- Gives good gloss and good flow

SYNOLAC® 20108S-65

FORMULATION GUIDELINES

RECOMMENDATIONS FOR USE

SYNOLAC® E20108-65 is used in the coil coating industry for cost effective backers and exterior topcoats. SYNOLAC® E20108-65 based coatings should be modified with hexamethoxymethylmelamine (HMMM) at a resin solids ratio of between 80:20 and 90:10 polyester: amino resin. A typical curing schedule is 2 minutes at 260°C peak metal temperature. The temperature and times will vary according to the type and gauge of the metal substrate being used. The addition of a catalyst such as Nacure 3525 at 0.1 - 0.2% can assist in increasing cure rate. The use of Beetle BE672 at 80:20 polyester: amino resin solids ratio can be used for low temperature curing (e.g. 20 minutes at 120°C metal temperature)

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 20108S-65 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided. In the above mentioned storage conditions the shelf life of the resin will be from the date of manufacturing.
Shelf Life (Months): 12

Arkema Chemical India Private Ltd.
D-43, Trans Thane Creek MICD
Industrial Area 400706, Mumbai – India
T +91 22 67377122

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

ARKEMA