

## TECHNICAL DATA SHEET

# SYNOLAC® 2700 WD 70

*Solventborne Silicone Alkyd*

### PRODUCT APPLICATION DETAILS

SYNOLAC® 2700 WD 70 is an air drying silicone modified isophthalic alkyd recommended for high durability exterior marine and decorative maintenance finishes.

SYNOLAC® 2700 WD 70 is used as the sole binder for high durability and temperature resistant coatings on stable substrates (e.g. masonry, plasters, structural steel, exterior cladding repair coats).

SYNOLAC® 2700 WD 70 can also be used, in combination with suitable alkyds or thixotropic alkyds, for high durability exterior wood coatings. It is recommended that SYNOLAC® 2700 WD 70 is used at between 45-55% of the total binder solids in order to obtain the improved durability and the flexibility necessary for wood coatings.

SYNOLAC® 2700 WD 70 is supplied in low aromatic white spirit to enable the formulation of coatings that do not require adverse environmental labelling.

### SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C)	68 - 72 %	ISO 3251
Viscosity (Brookfield SC4-21/13R) (20°C)	6000 - 8300 mPa.s	ISO 3219
Color	6 max Gardner	ISO 4630
Acid value	10 max mg KOH/g	ISO 2114

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Solvent	Low aromatic white spirit	-
Flash point	40 °C	ISO 3679
Density	0.96 g/ml	ISO 2811
Fatty acid type	Special	-
Silicone content	30 %	-

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### MARKETS & APPLICATIONS

#### Coatings & Inks

- Architectural Coating
  - Specialty Coatings
  - Stains
  - Trim
  - Architectural Wood
- Industrial Coating
  - General Industry

### PERFORMANCE BENEFITS

- Excellent weather resistance up to 15 years
- Low dirt retention
- Good brushing and drying characteristics
- Low viscosity
- High build
- Excellent colour retention
- Excellent chalk resistance

# SYNOLAC® 2700 WD 70

## FORMULATION GUIDELINES

### **DRIERS**

SYNOLAC® 2700 WD 70 requires metal driers to accelerate the autoxidation process. A suitable combination of driers for use in systems containing SYNOLAC® 2700 WD 70 is : 0.06 % cobalt, 0.09 % zirconium and 0.1 % calcium calculated as metals on solid resin. Depending on the formulation (clear, pigmented, etc...) and on the application, the loading of each drier may be increased or reduced in order to achieve the appropriate drying/hardness profile. The use of an anti-skinning agent is essential to prevent in-can skinning of the finished product.

### **SOLUBILITY**

SYNOLAC® 2700 WD 70 is soluble in aromatic and aliphatic hydrocarbons, esters and ketones and partially soluble in alcohols.

### **COMPATIBILITY**

SYNOLAC® 2700 WD 70 is compatible with most medium and long oil alkyds and GELKYD® or SUPER GELKYD® thixotropic resins.

### **REMARKS**

The product may present some haziness after storage.

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

SYNOLAC® 2700 WD 70 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

**ARKEMA**