

TECHNICAL DATA SHEET

SYNOLAC® 4210W55

Medium oil alkyd

PRODUCT APPLICATION DETAILS

SYNOLAC® 4210W55 is a medium oil oxidizing alkyd that produces a wide range of high quality air drying finishes. It provides an excellent combination of fast drying and toughness, together with excellent colour retention and durability.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C, %)	54 - 56	ISO 3251
Viscosity (25°C, Gardner)	Z3Z4 - Z4Z5	Gardner-Holdt
Color (Gardner)	Max. 6	ASTM D-1544
Acid value (mg KOH/g)	Max. 12	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	White Spirit	-
Density (25°C, g/mL)	0.93	-
Fatty acid type	Vegetable Fatty Acid	-
Fatty acid content (%)	51	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS & APPLICATIONS

Coatings & Inks

- Architectural Coating
 - Primers
 - Trim
- Industrial Coating
 - Automotive - Refinish
 - General Industry
 - Wood Furniture
 - Industrial Wood Finishes

PERFORMANCE BENEFITS

- Excellent fast drying
- Excellent toughness
- Good durability
- Excellent color retention
- Good gloss retention

SYNOLAC® 4210W55

FORMULATION GUIDELINES

RECOMMENDATIONS FOR USE

SYNOLAC® 4210W55 is recommended for all types of transport and car refinishing, but can also be used for undercoats and semi-gloss enamels.

In air drying applications the recommended driers are 0.05% Cobalt, 0.15% Zirconium, and up to 0.2% Calcium, all expressed as metals on solid resin.

SOLUBILITY

Aromatic hydrocarbon — Complete
Aliphatic Hydrocarbon — Complete
Ester — Complete
Ketone — Complete
Ether Alcohol — Complete
Alcohol — Partial

COMPATIBILITY

Long Oil Alkyd — Very Good
Medium Oil Alkyd — Very Good
Drying Oil — Very Good
Oleo-resinous Varnishes — Fair
Chlorinated Rubber — Fair
Amino Resin — Fair
Short Oil Alkyd — Fair

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 4210W55 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 35°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 12 months.

Arkema Coating Resins Malaysia
PLO 491, Jalan Keluli, Pasir Gudang
Industrial Estate, 81700 Pasir Gudang,
Johor – Malaysia
T +60 7 253 6688

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

ARKEMA