

TECHNICAL DATA SHEET

SYNOLAC® 5069S-65

Oil free polyester

PRODUCT APPLICATION DETAILS

SYNOLAC® 5069S-65 is a saturated polyester developed for use in coil coating, sheet fade metal decorating and general industrial applications.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (at 150°C, 1gm, 1hr)	63 - 67 %	ISO 3251
Viscosity (at 25°C)	25 - 35 P	
Color	2 max Gardner	ISO 4630
Acid value	10 max mg KOH/g	ISO 2114
Hydroxyl value	25 - 35	

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Volatile	Aromatic Solvent 150	
Density (at 20°C)	1.06 g/ml	ISO 2811

Acid value and/or Hydroxyl value quoted relative to solid resin

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - Coil
 - Protective Coating

PERFORMANCE BENEFITS

- Good gloss & flow
- Good hardness
- Good flexibility
- Good durability

SYNOLAC® 5069S-65

FORMULATION GUIDELINES

RECOMMENDATIONS FOR USE

SYNOLAC® 5069S-65 is compatible with a wide range of melamine resins and is typically used with hexamethoxymethyl melamine and partially methylated melamine.

SYNOLAC® 5069S-65 with hexamethoxymethyl melamine resin at ratio of 70:30 to 85:15 on solid resin content is suggested. To promote cure use of between 1% and 5% of acid catalyst is recommended, e.g., paratoulene sulphonic acid, calculated on melamine solids.

Variation in the level of SYNOLAC® 5069S-65 and the type of amino resin will modify the overall performance characteristics of the coating. Increasing the level of amino resin (and catalyst) will generally tend to increase the hardness and solvent resistance of the coating but may compromise the flexibility. For coil coating applications 85:15 to 80:20 ratio on solid with hexamethoxymethyl melamine resin is recommended blend on solids of 72:18:10 OFPE: Melamine: Epoxy Resin (epoxy equ »500) with 2% on amino solid is suitable. Part methylated amino resin can be use in place of hexamethoxymethyl melamine and will develop very good hardness & solvent resistance but at the expense of flexibility.

Benzoguanamine resin can also use to increase cure response and retortability. General industrial enamels can be formulated with 70:30 to 80:20 ratios with hexamethoxymethyl melamine or part methylated melamine, with 2% PTSA catalyst on amino solids. This resin can be used in combination with Isocyanates. Enamel based on SYNOLAC® 5069S-65 exhibit good light fastness results after prolonged UV exposure and finishes are resistant to staining from a variety of households materials.

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 5069S-65 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided. In the above mentioned storage conditions the shelf life of the resin will be from the date of manufacturing.

Shelf Life (Months): 12

Arkema Chemical India Private Ltd.
D-43, Trans Thane Creek MICD
Industrial Area 400706, Mumbai – India
T +91 22 67377122

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790