

TECHNICAL DATA SHEET

SYNOLAC® 5086

Polyester polyol

PRODUCT APPLICATION DETAILS

SYNOLAC® 5086 is a low viscosity linear saturated polyester with good compatibility designed for blending with other systems in order to increase solids and reduce volatile organic contents.

SYNOLAC® 5086 is a highly versatile resin that can be used in diverse end-uses such as 2-component acrylic isocyanate or polyester isocyanate systems and high quality stoving systems.

SYNOLAC® 5086 will react into the blended system via its high hydroxyl content, and will not compromise durability.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Viscosity (25°C)	5500 - 8500 mPa.s	ISO 3219
Color	300 max Hazen	ISO 6271
Acid value	7 max mg KOH/g	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Density	1.12 g/ml	-
Hydroxyl content	5,7 - 6,7 %	-
Hydroxyl equivalent weight	190 - 220	-
Solids content	100 %	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - Automotive - OEM
 - Automotive - Refinish
 - General Industry
 - Protective And Marine Coating

PERFORMANCE BENEFITS

- Reduce volatile organic content
- Increase solids content
- Improve flexibility and toughness at low temperatures

SYNOLAC® 5086

FORMULATION GUIDELINES

RECOMMENDATIONS FOR USE

It is suggested that initial evaluations be carried out using SYNOLAC® 5086 at a substituted level of 20% of the main binder.

(a) 2-component systems

When used in combination with other hydroxyl containing resins in 2-component systems, SYNOLAC® 5086 will react with aromatic isocyanates such as Desmodur® L series ⁽¹⁾ and aliphatic isocyanates such as Tolonate™ HDB series ⁽²⁾ and Desmodur® N series ⁽¹⁾.

Recommended ratios using typical isocyanates would be:

The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants.

The relationship is:

Hydroxyl Equivalent Weight = $(17 \times 100) / \%OH$

Isocyanate Equivalent Weight = $(42 \times 100) / \%NCO$

(b) stoving systems

When used in combination with other resins in stoving systems, SYNOLAC® 5086 will react with most melamine resins, resin solids ratios of between 70:30 and 85:15 binder to amino are suggested.

SOLUBILITY

SYNOLAC® 5086 is completely soluble in aromatic hydrocarbons, esters and ketones and insoluble in aliphatic hydrocarbons.

COMPATIBILITY

SYNOLAC® 5086 is compatible with many resins including polyesters, acrylics, isocyanates, melamine, urea and alkyd resins.

Notes: ⁽¹⁾ Bayer MaterialScience, ⁽²⁾ VENCOR®ex Chemicals

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 5086 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790