

TECHNICAL DATA SHEET

SYNOLAC® 8021 X 70

Short Oil Alkyd

PRODUCT APPLICATION DETAILS

SYNOLAC® 8021 X 70 is a short oil high solid air drying alkyd.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C)	68 - 72 %	ISO 3251
Viscosity (25°C)	5000 - 8000 mPa.s	ISO 3219
Color	6 max Gardner	ISO 4630
Acid value	10 max mg KOH/g	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Xylene	-
Flash point	28 °C	ISO 3679
Density	1.04 g/ml	ISO 2811
Fatty acid type	Linoleic rich	-
Fatty acid content	33 %	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
- General Industry

SYNOLAC® 8021 X 70

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 8021 X 70 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

ARKEMA