

TECHNICAL DATA SHEET

SYNOLAC® 8026 X 60

Short Oil Alkyd

PRODUCT APPLICATION DETAILS

SYNOLAC® 8026 X 60 is a short oil alkyd resin based on soya rich oil, designed for the formulation of nitrocellulose lacquers and varnishes, very fast drying sealers, fillers and primers with easy sanding, very fast air drying varnishes and paints, two pack polyurethane lacquers and general purpose stoving enamels.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C)	59 - 61 %	ISO 3251
Viscosity (Brookfield SC4-25/13R, 6.6s-1) (25°C)	3100 - 6000 mPa.s	ISO 3219
Color	6 max Gardner	ISO 4630
Acid value	15 max mg KOH/g	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Xylene	-
Flash point	25 °C	ISO 3679
Density	1 g/ml	ISO 2811
Fatty acid type	Soya	-
Fatty acid content	27 %	-
Hydroxyl content	3 %	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - Wood Furniture
 - Industrial Wood Finishes

SYNOLAC® 8026 X 60

FORMULATION GUIDELINES

RECOMMENDATIONS FOR USE

SYNOLAC® 8026 X 60 is recommended for nitrocellulose lacquers and varnishes formulations with and alkyd/ nitrocellulose ratio till 3:1. An important characteristic is a very quick solvent release from the applied film, allowing to handle the varnished goods in very short times. Quantities of 1-3% of zinc stearate are recommended to obtain a good sanding. On matting varnishes, allows a perfect distribution on the varnish surface, giving an excellent appearance.

SYNOLAC® 8026 X 60 allows formulation of nitrocombined varnishes which may be hardened with polysocyanates. Very good stackability and sanding.

SOLUBILITY

SYNOLAC® 8026 X 60 is soluble in aromatic hydrocarbons, esters, ketones, glycol ethers, alcohols and trichloro-ethylene. It has a limited solubility in terpenic solvents and it is insoluble in aliphatic hydrocarbons.

COMPATIBILITY

SYNOLAC® 8026 X 60 is compatible with nitrocellulose, chlorinated rubber resins, maleic resins and polyisocyanates, partially compatible with phenolic modified resins, drying oils. It is incompatible with standoils.

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 8026 X 60 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790