

TECHNICAL DATA SHEET

SYNOLAC® 8086 X 50 (Formerly CHEMPOL® 809-6886)

PRODUCT APPLICATION DETAILS

SYNOLAC® 8086 X 50 is a chain-stopped short oil alkyd with fast air-dry times for light industrial metal coatings, implement enamels, and transportation finishes.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	50 %	-
Viscosity	Y-Z1 Gardner Holdt	-
Reduced viscosity (40% in Xylene)	F-I	-
Color	7 Gardner	-
Acid value	16 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Xylene	-
Density	8.3 lbs/gal	-
Hydroxyl content	3.2 %	-
Hydroxyl number	105	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - General Industry

SYNOLAC[®] 8086 X 50 (Formerly CHEMPOL[®] 809-6886)

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC[®] 8086 X 50 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

ARKEMA