

TECHNICAL DATA SHEET

SYNOLAC® 8213 BA 75 (Formerly CHEMPOL® 816-0136)

PRODUCT APPLICATION DETAILS

SYNOLAC® 8213 BA 75 is a high solids conjugated fatty acid-modified epoxy with good adhesion, color retention, durability, and chemical, humidity, and salt spray resistance, for use in metal primers.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	75 %	-
Viscosity	Z1-Z3 Gardner Holdt	-
Reduced viscosity (60% in n-Butyl Acetate)	J-L	-
Color	8 Gardner	-
Acid value	10 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	n-Butyl acetate	-
Density	8.7 lbs/gal	-
Hydroxyl content	3.4 %	-
Hydroxyl number	112	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Architectural Coating
 - Exterior Wall
- Industrial Coating
 - Automotive - OEM
 - General Industry
 - Protective Coating

PERFORMANCE BENEFITS

- Good Color Retention
- Good Exterior Durability
- Good Salt Spray Resistance
- Very Good Adhesion to Metals
- Good Humidity Resistance
- Excellent Chemical Resistance

SYNOLAC® 8213 BA 75 (Formerly CHEMPOL® 816-0136)

FORMULATION GUIDELINES

RECOMMENDATIONS OF USE

Metal – Primer Coatings

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 8213 BA 75 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790