

TECHNICAL DATA SHEET

SYNOLAC® 8218 S 75 (Formerly CHEMPOL® 812-2218)

Modified alkyd

PRODUCT APPLICATION DETAILS

SYNOLAC® 8218 S 75 is a high solids phenolic-modified soya short oil alkyd with good corrosion and humidity resistance for use in metal primers. SYNOLAC® 8218 S 75 is the HAPs-free version of SYNOLAC® 8204 X 75.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	75 %	-
Viscosity	Z-Z2 Gardner Holdt	-
Reduced viscosity (60% in Xylene)	E-H	-
Color	12 Gardner	-
Acid value	24 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	n-Butyl acetate/MAK 89.2/10.8	-
Density	8.8 lbs/gal	-
Hydroxyl content	2.2 %	-
Hydroxyl number	72	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - General Industry
 - Protective Coating

PERFORMANCE BENEFITS

- Excellent Compatibility with Chain Stopped and Monomer Modified Alkyds
- Good Corrosion Resistance
- Good Humidity Resistance
- Rapid Viscosity Reduction
- HAPS Free SYNOLAC® 8204 X 75

SYNOLAC® 8218 S 75 (Formerly CHEMPOL® 812-2218)

FORMULATION GUIDELINES

RECOMMENDATIONS OF USE

Metal—Primer Coatings
Metal—High Gloss Industrial Primers
Lacquer Resistant and Non-Lift Primers
Can be used with Melamine or Urea Resins for Bake Applications
Can be used with Isocyanates for Chemical Resistant Primers

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 8218 S 75 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

ARKEMA