

TECHNICAL DATA SHEET

SYNOLAC® 8250 X 60

Modified alkyd

PRODUCT APPLICATION DETAILS

SYNOLAC® 8250 X 60 is a styrenated short oil soya alkyd resin.
SYNOLAC® 8250 X 60 is recommended for very fast air drying spraying finishes, paints with good resistance to water and mineral oils and primers for crankcases.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C)	59 - 61 %	ISO 3251
Viscosity (Brookfield SC4-25/13R, 6.6s-1) (25°C)	3100 - 4300 mPa.s	ISO 3219
Color	7 max Gardner	ISO 4630
Acid value	15 max mg KOH/g	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Xylene	-
Flash point	25 °C	ISO 3679
Density	0.98 g/ml	ISO 2811
Fatty acid type	Soya	-
Fatty acid content	30 %	-
Typical weight per epoxide	Styrene	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - General Industry
 - Protective And Marine Coating

PERFORMANCE BENEFITS

- Excellent surface drying
- Very good hardening in depth
- Good resistance to water and mineral oils

SYNOLAC® 8250 X 60

FORMULATION GUIDELINES

DRIERS

The recommended drier level for use on air drying systems is 0.03% cobalt as metal on solids resin. Depending on the formulation (clear, pigmented, thixotropic, etc...) and on the application, the loading of each drier may be increased or reduced in order to achieve the appropriate drying/hardness profile.

The use of antiskinning agent is essential to prevent in-can skinning of the finished product.

We advice to check the stability of the paints based on basic pigments.

COMPATIBILITY

SYNOLAC® 8250 X 60 is compatible with hydrocarbon resins, partially compatible with drying oils, maleic resins and modified phenolic resins. It is incompatible with standoils, long and medium oil alkyd resins, melamine/formaldehyde resins and chlorinated rubber resins.

SOLUBILITY

SYNOLAC® 8250 X 60 is soluble in aromatic hydrocarbons, esters, ketones and glycol ethers, partially soluble in terpenics and insoluble in alcohols.

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 8250 X 60 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790