

## TECHNICAL DATA SHEET

# SYNOLAC® 8335 S 75 (Formerly CHEMPOL® 813-1435)

Modified alkyd

### PRODUCT APPLICATION DETAILS

SYNOLAC® 8335 S 75 is a high solids styrene-modified soya/DCO oil alkyd with fast tack-free and dry-through times, for use in a broad range of industrial coatings.

### SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	75 %	-
Viscosity	Z3-Z5 Gardner Holdt	-
Reduced viscosity (60% in n-Butyl Acetate)	N-R	-
Color	8 Gardner	-
Acid value	8 mg KOH/g	-

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Solvent	n-Butyl acetate/MAK	-
Density	8.4 lbs/gal	-
Hydroxyl content	1.2 %	-
Hydroxyl equivalent weight	1400	-
Hydroxyl number	40	-

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### MARKETS

#### Coatings & Inks

- Industrial Coating
  - Ace
  - Automotive - OEM
  - Automotive - Refinish
  - General Industry
  - Protective Coating
  - Automotive And Transportation

### PERFORMANCE BENEFITS

- Fast tack free time
- Fast through dry

# SYNOLAC® 8335 S 75 (Formerly CHEMPOL® 813-1435)

## FORMULATION GUIDELINES

### RECOMMENDATIONS OF USE

Very good exterior durability

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

SYNOLAC® 8335 S 75 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

**Arkema Coating Resins**  
410 Gregson Dr.  
Cary, NC 27511 – USA  
T +1 919 469 6700

**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790