

## TECHNICAL DATA SHEET

# SYNOLAC® 8661 S 70 (Formerly CHEMPOL® 801-7961)

Solventborne Alkyd

### PRODUCT APPLICATION DETAILS

SYNOLAC® 8661 S 70 is a high solids long oil alkyd for exterior porch and deck stains.

### SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	70 %	-
Viscosity	Z1-Z3 Gardner Holdt	-
Color	7 Gardner	-
Acid value	10 mg KOH/g	-

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Solvent	Xylene/A100/Mineral spirits (4.5/28.2/67.3)	-
Density	8.05 +/- 0.1 lbs/gal	-

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### MARKETS

#### Coatings & Inks

- Architectural Coating
  - Exterior Wall
  - Primers
  - Specialty Coatings
  - Stains
  - Trim
- Flooring
  - Floor Polish & Floor Coatings
- Industrial Coating
  - General Industry

# SYNOLAC® 8661 S 70 (Formerly CHEMPOL® 801-7961)

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

SYNOLAC® 8661 S 70 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

**Arkema Coating Resins**  
410 Gregson Dr.  
Cary, NC 27511 – USA  
T +1 919 469 6700

**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

**ARKEMA**