

TECHNICAL DATA SHEET

SYNOLAC® 8902 (Formerly CHEMPOL® 211-1902)

PRODUCT APPLICATION DETAILS

SYNOLAC® 8902 is a TMPD maleate solution in dioctyl terephthalate plasticizer.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	80 %	-
Viscosity	500-700 cP	-
Color	4 Gardner	-
Acid value	6 mg KOH/g	-

MARKETS

Coatings & Inks

- Industrial Coating
 - General Industry

PERFORMANCE BENEFITS

- TMPD maleate solution in dioctyl terephthalate plasticizer

SYNOLAC® 8902 (Formerly CHEMPOL® 211-1902)

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 8902 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790