SYNOLAC®

TECHNICAL DATA SHEET

SYNOLAC® 9715 S 65 *(Formerly CHEMPOL® 211-8915)*

Oil free polyester

PRODUCT APPLICATION DETAILS

SYNOLAC® 9715 S 65 is a high performance polyester in exempt solvent for industrial, military, and aerospace coatings.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	65 %	-
Viscosity	Z1-Z2 Gardner Holdt	-
Color	9 Gardner	-
Acid value	6 mg KOH/g	-

OTHER CHARACTERISTICS[1]

	CHARACTERISTICS	METHODS
Solvent	t-BAc/Xylene	-
Density	9 lbs/gal	-
Hydroxyl content	2.2 %	-
Hydroxyl number	72	-

[1] The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
  - Automotive - OEM
  - General Industry
  - Protective And Marine Coating

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 9715 S 65 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on https://www.arkema.com/global/en/products/product-safety/disclaimer/ which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

arkema.com