

TECHNICAL DATA SHEET

UNITHANE® 655W55 MY

Modified alkyd

PRODUCT APPLICATION DETAILS

UNITHANE® 655W55 MY is an urethane alkyd designed for use in clear and pigmented finishes as the sole medium or in combination with long oil alkyds.

UNITHANE® 655W55 MY can be used in decorative gloss or eggshell finishes and should comprise between 20-50 % of the media, the balance being a suitable long oil alkyd. In thixotropic decorative gloss and eggshell finishes, similar percentages can be used.

In floor varnishes and related finishes, UNITHANE® 655W55 MY is recommended for use as the sole medium.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C, %)	54 - 56	ISO 3251
Viscosity (25°C, Gardner)	XY - YZ	Gardner-Holdt
Color (Gardner)	Max. 6	ASTM D-1544
Acid value (mg KOH/g)	Max. 3	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	White Spirit	-
Density (25°C, g/mL)	0.92	-
Fatty acid type	Soya Bean Oil	-
Fatty acid content (%)	61	-
Modification	Urethane	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS & APPLICATIONS

Coatings & Inks

- Architectural Coating
 - Deck Restoration
 - Stains
 - Trim
 - Architectural Wood
- Industrial Coating
 - General Industry
 - Marine
 - Protective And Marine Coating
 - Wood Furniture
 - Wood Parquet
 - Industrial Wood Finishes

PERFORMANCE BENEFITS

- Fast drying time
- Good abrasion resistance
- Excellent gloss retention

UNITHANE® 655W55 MY

FORMULATION GUIDELINES

DRIERS

UNITHANE® 655W55 MY can be formulated to produce air drying paints when suitably modified with the following drier metals: cobalt: 0.05%, calcium: 0.2%, zirconium: 0.15% as % metal on solid resin. Depending on the formulation (clear, pigmented, thixotropic, etc...) and on the application, the loading of each drier may be increased or reduced in order to achieve the appropriate drying/hardness profile.

The use of antiskinning agent is essential to prevent in-can skinning of the finished product.

SOLUBILITY

UNITHANE® 655W55 MY is soluble in aliphatic and aromatic hydrocarbons, esters and ketones.

COMPATIBILITY

UNITHANE® 655W55 MY is compatible with medium and long oil alkyds and thixotropic resins.

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

UNITHANE® 655W55 MY should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 35°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 12 months.

Arkema Coating Resins Malaysia
PLO 491, Jalan Keluli, Pasir Gudang
Industrial Estate, 81700 Pasir Gudang,
Johor – Malaysia
T +60 7 253 6688

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

ARKEMA